

# BISCO® HT-6220

BISCO® HT-6220 soft silicone material is a part of the performance grade solid silicone series. The material's low Shore A durometer, high tear strength, and extremely tight thickness tolerances offer added benefits for sealing.

## Features & Benefits:

- Provides low closure force
- Bridges the gap between foams and high durometer solids

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
<b>PHYSICAL</b>			
Color	Visual	Black	---
Thickness, mm (inches)	Internal	<b>0.250 - 3.18</b> <b>(0.013 - 0.125)</b>	---
Specific Gravity, (g/cc)	Internal	1.08	---
Durometer, Shore A	ASTM D2240	20	<b>22 ± 5</b>
Compression Set, %	ASTM D395 150°C (302°F) / 70 hrs / 25%	< 25	---
Tensile Strength, MPa (psi)	ASTM D412	4.4 (640)	<b>&gt; 3.45</b> <b>(&gt; 500)</b>
Elongation, %	ASTM D412	580	<b>&gt; 400</b>
Tear Resistance, ppi	ASTM D624	116	<b>&gt; 40</b>

Specification values in bold are tested on a batch basis.

Further industry specifications tested in tables below.

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
<b>ELECTRIC</b>			
Dielectric Strength, Volts/mil	ASTM D149	374	---
Dielectric Constant, 1 kHz	ASTM D150	2.97	---
Dissipation Factor, 1 kHz	ASTM D495	0.003	---
Dry Arc Resistance, Seconds	ASTM D495	123	---
Volume Resistivity, Ohm-cm	ASTM D257	10 <sup>14</sup>	---

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
<b>THERMAL</b>			
Temperature Range, °C (°F)	Internal	-55 to +200 (-67 to +392)	---
Thermal Conductivity, W/m °K	ASTM D518	0.22	---
Low Temperature Brittleness	ASTM D2137 -62°C (-80°F) / 3 min	Pass	---

#### Standard Thickness Tolerances

NOMINAL THICKNESS	TOLERANCE
mm (inches)	mm (inches)
0.254 (0.010)	± 0.051 (± 0.002)
0.508 (0.020)	+ 0.076/- 0.051 (+ 0.003/- 0.002)
0.787 (0.031)	± 0.102 (± 0.004)
1.600 (0.063)	± 0.152 (± 0.006)
3.175 (0.125)	± 0.203 (± 0.008)

#### Width Tolerances

NOMINAL WIDTH	TOLERANCE
mm (inches)	mm (inches)
> 660 - 914 (> 26 - 36)	+ 25.4/- 0 (+ 1/- 0)

#### Notes:

\*Typical Value- Value is based on historical data. Please note the frequency of testing varies.

\*\*Specification- Applies to physical properties only, which are based on Rogers' internal benchmark and standard BISCO specification values.

Additional industry specifications are available as well. All other properties are based on industry standard guidelines.

All metric conversions are approximate. Reference US customary units for official values and tolerances.