

## Typical Properties of BDJN 400

Polymer	Crosslinked Polyethylene/EVA		
Physical Property	Test Method	Result (US Units)	Result (Metric Units)
Density	ASTM D3575	4 pcf	64 Kg/m <sup>3</sup>
Compression Deflection 25%	ASTM D3575	13 psi	89.6 kPa
Compression Set 50%	ASTM D3575	16%	16%
Tensile Strength	ASTM D3575	90 psi	620.5 kPa
Elongation	ASTM D3575	340%	340%
Tear Strength	ASTM D3575	21 lb/in	3.67 kN/m
Thermal Stability	ASTM D3575	2% Max	2% Max
Flammability	FMVSS-302	Pass @ .250" or Thicker	
Service Temperature	-65 to 210F		

Contact customer service for specification inquiries.

*Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.*