

Typical Properties of **EVAZOTE® EV45CN**

Polymer	Crosslinked EVA		
Physical Property	Test Method	Result (US Units)	Result (Metric Units)
Density	ISO 7214	3.12 pcf	50 kg/m ³
Compression Deflection 25%	ISO 7214	8.84 psi	61 kPa
Compression Deflection 50%	ISO 7214	18.5 psi	128 kPa
Compression Set 50%	ISO 7214	14.5%	14.5%
Tensile Strength	ISO 7214	83.4 psi	575 kPa
Elongation	ISO 7214	170%	170%
Tear Strength	ISO 8067	7 lb/in	1240 N/m
Flammability	FMVSS-302	Pass @ .196" or Thicker	
Service Temperature	-94 to 149 F		
Thermal Conductivity	ASTM C518	K Factor .263	
Volume Resistivity	ASTM D991-89	10 ³ ohm.cms	

Contact customer service for specification inquiries.

Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.