

## Typical Properties of SCE42NEO

Polymer	Neoprene Based		
ASTM D1056 Classification	2C2		
ASTM D1056 Suffix Compliances	B3, C1, C2, F1, M		
ASTM D6576 Classification	Type II A,B Soft/Med		
Physical Property	Test Method	Result (US Units)	Result (Metric Units)
Density	ASTM D1056	7 – 11 pcf	112 – 176 kg/m <sup>3</sup>
Compression Deflection 25%	ASTM D1056	5 – 9 psi	34.5 – 62 kPa
Compression Set 50%	ASTM D1056	30% Max	30% Max
Fluid Immersion	ASTM D1056	250% Max	250% Max
Water Absorption	ASTM D1056	5% Max	5% Max
Tensile Strength	ASTM D412	65 psi Min	448 kPa Min
Elongation	ASTM D412	125% Min	125% Min
Tear Strength	ASTM D624	12 lb/in Min	2.1 kN/m Min
Resilience	ASTM D2632	10 - 20 %	10 - 20 %
CD after Oven Aging	ASTM D1056	30% Max	30% Max
Flammability	FMVSS-302	Pass @ .125" or Thicker	
Service Temperature	-40 to 150 F		
High Intermittent Temperature	200 F		
Thermal Conductivity	ASTM C518	K Factor .38	

UL Listings <sup>1</sup>	
Gasketing and Sealing	UL508, UL50, UL50E, UL48

<sup>1</sup> Contact customer service for specification inquiries and UL Information.

*Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.*