

Typical Properties of DK1111 RL1

Polymer	Neoprene/EPDM		
ASTM D1056 Classification	2C1		
ASTM D1056 Suffix Compliances	A1, B2, B3, C1, C2, F1, M		
ASTM D6576 Classification	Type II A,B Soft		
Physical Property	Test Method	Result (US Units)	Result (Metric Units)
Density	ASTM D1056	4 – 8 pcf	64 - 128 kg/m ³
Compression Deflection 25%	ASTM D1056	2 – 5 psi	13.8 – 34.5 kPa
Compression Set 50%	ASTM D1056	25% Max	25% Max
Water Absorption	ASTM D1056	5% Max	5% Max
Tensile Strength	ASTM D412	75 psi Min	517 kPa Min
Elongation	ASTM D412	150 % Min	150 % Min
CD after Oven Aging	ASTM D1056	30% Max	30% Max
Fluid Immersion	ASTM D1056	250% Max	250% Max
Flammability	FMVSS-302	Pass @ .040" or Thicker	
Service Temperature	-40 to 250 F		
Thermal Conductivity	ASTM C518	K Factor .27	

UL Listings ¹	
Gasketing and Sealing	UL508, UL157, UL50E
Flammability	UL-94 HF-1

¹ Contact customer service for specification inquiries and UL Information.

Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

