

PORON® 4701-30 Very Soft – Data Sheet

PROPERTY	TEST METHOD	VALUE		
<b>PHYSICAL</b>				
Density, kg /m <sup>3</sup> (lb / ft <sup>3</sup> )	ASTM D 3574-95, Test A	240 (15)	320 (20)	400 (25)
Tolerance, %		± 10		
Thickness, mm (inches)		4.78 – 12.70 (0.188 - 0.500)	1.57 – 3.18 (0.062-0.125)	0.79 – 1.14 (0.031 - 0.045)
Tolerance, %		± 10		± 15
Standard Color (Code)		Black (04)		
Compression Force Deflection, kPa (psi) Typical kPa, (psi)	0.51cm/min (0.2" / min) Strain Rate Force Measured @ 25% Deflection	7 - 35 (1 – 5) 21 (3)	21 - 55 (3 – 8) 35 (5)	35 - 83 (5 – 12) 62 (9)
Hardness, Durometer, Shore "O", Shore "A"	ASTM D 2240-97	<3 <3	8 5	16 12
Compression Set, % max.	ASTM D 1667-90 Test D @ 23°C (73°F) ASTM D 3574-95 Test D @ 70°C (158°F) ASTM D 3574-95 Test J/Test D autoclaved 5 hrs @ 121°C (250°F)	2 10 5		
Dimensional Stability, % max. change	22 hrs @ 80°C (176°F) in a forced-air oven	± 1		
Tensile Strength, kPa (psi) min. Typical kPa (psi)	ASTM D 3574-75 Test E	138 (20) 207 (30)	207 (30) 346 (50)	242 (35) 484 (70)
Tensile Elongation, % min., Typical	ASTM D 3574-75 Test E	100 160	100 155	100 150
Tear Strength, kN/m (pli) min Typical kN/m (pli)	ASTM D 264-91 Die C	0.2 (1) 0.9 (5)	0.5 (3) 1.2 (7)	0.7 (4) 1.8 (10)
<b>ELECTRICAL AND THERMAL</b>				
Dielectric Constant, K' ("DK")	ASTM D 150 measurements at 22°C (72°F) relative humidity 50% for 24 hrs.	1.75		
Dielectric Strength, kV/m (volts/mil)	ASTM D 149-97a	1969 (50)		
Dissipation Factor, tan D ("DF")	ASTM D 150-98	0.05		
Volume Resistivity, ohm-cm (ohm-in)	ASTM D 257-99	3 x 10 <sup>11</sup> (1.18 x 10 <sup>11</sup> )		
Surface Resistivity, ohm/sq.	ASTM D 257-99	6 x 10 <sup>11</sup>		
Thermal Conductivity, W/m-C (BTU-in./hr/ft <sup>2</sup> -F)	ASTM C 518-98	-	0.076 (0.53)	-
Coefficient of Thermal Expansion		2.3-3.1 x 10 <sup>-4</sup> in/in/°C (1.3-1.7 x 10 <sup>-4</sup> in/in/°F)		

The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' PORON Materials for each application. The Rogers logo, Helping power, protect, connect our world and PORON are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2008, 2014, 2016, 2017 Rogers Corporation, All rights reserved. Printed in U.S.A. 1217-PDF, Publication # 17-006

PORON® 4701-30 Very Soft, Continued

PROPERTY	TEST METHOD	VALUE		
<b>TEMPERATURE RESISTANCE</b>				
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)		
Recommended Intermittent Use, max.		121°C (250°F)		
Embrittlement	ASTM D 746-98	-51°C (-60°F)		
Cold Flexibility	MIL-P-12420D 1991 @ -40°C (-40°F)	Pass		
<b>FLAMMABILITY AND OUTGASSING</b>				
Flammability, mm (inches)	UL 94HBF (File E20305) (Pass ≥)	4.8 (0.188)	2.4 (0.093)	-
	MVSS 302 (Pass ≥)	4.8 (0.188)	1.6 (0.062)	1.6 (0.062)
	CSA Comp HBF (File 188149) (Pass ≥)	4.8 (0.188)	2.4 (0.093)	-
Fogging	SAE J-1756 3 hrs @ 100°C (212°F)	Pass		
Outgassing, Total Mass Loss (TML) %	ASTM E 595-93 24 hrs @ 125°C (257°F) @ <7kPa (1.02 psi)	0.8	1.0	1.3
Outgassing, Collected Volatile Condensable Materials (CVCM) %		0.1	0.1	0.2
Outgassing, Water Vapor Regain (WVR) %		0.2	0.3	0.6
<b>ENVIRONMENTAL</b>				
Gasketing and Sealing	UL JMST2 (Consisting of UL50 and UL508) CAN/CSA – C22.2 No. 94-M91	File MH15464 File 188149		
Water Absorption, High Humidity Exposure, % weight gain, typical	AMS 3568-95	2		
Water Absorption, Immersion Testing, % weight gain, typical	ASTM D 570-95	12	9	14
UV Resistance	ASTM G 53-96	Good		
Ozone Resistance	GM 4486P-95	Pass	Pass	-
Corrosion Resistance	AMS 3568-91	Pass		
Mildew/Bacteria Resistance	ASTM G 21	Good		
Staining	ASTM D 925	No Stain		

Notes:

- – Represents testing not available at this time.
- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' PORON Materials for each application. The Rogers logo, Helping power, protect, connect our world and PORON are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2008, 2014, 2016, 2017 Rogers Corporation, All rights reserved. Printed in U.S.A. 1217-PDF, Publication # 17-006