



Product Data Sheet



PORON® 4701-50 Firm Thin as Cast

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, kg/m ³ (lb./ft ³)	ASTM D 3574-95, Test A	480 (30)
Tolerance, %		± 10
Thickness, mm (inches)		0.43 - 0.50 (0.017 - 0.020)
Tolerance, mm (inches)		0.08 (± 0.003)
Standard Color (Code)		Black (04)
Compression Force Deflection, kPa (psi)		
Range kPa (psi)	0.51 cm/min (0.2"/min)	103 - 310 (15 - 45)
Typical kPa (psi)	Strain Rate Force Measured @ 25% Deflection	221 (32)
Hardness, Durometer Shore O	ASTM D2240-97	55
Compression Set, % max	ASTM D1667-90 Test D @ 23°C (73°F)	5
	ASTM D3574-95 Test D @ 70°C (158°F)	10
	ASTM D3574-95 Test J/Test D Autoclaved 5 hrs @ 121°C (250°F)	5
Dimensional Stability, % max change	22 hrs @ 80°C (176°F) in a Forced-Air Oven	± 1
Tensile Strength, min. kPa (psi)	ASTM D3574-75 Test E	1106 (160)
Tensile Elongation, % min.	ASTM D3574-75 Test E	90
Tear Strength, min. kN/m, (pli) Typical kNm, (pli)	ASTM D264-91 Die C	1.6 (9) 4.4 (25)



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2025 Rogers Corporation. All rights reserved.

0825-PDF • Publication #17-026PC www.rogerscorp.com

PROPERTY	TEST METHOD	VALUE
ELECTRICAL & THERMAL		
Dielectric Constant, K' ("DK")	ASTM D150 @ 22°C (72°F) Relative Humidity 50% for 24 hrs	1.63
Dielectric Strength, kV/m (volts/mil)	ASTM D149-97a	1969 (50)
Dissipation Factor, tan D ("DF")	ASTM D150-98	0.05
Volume Resistivity, ohm-cm (ohm-in)	ASTM D257-99	2 x 10 ¹² (7.87x 10 ¹¹)
Surface Resistivity, ohm/sq.	ASTM D257-99	7 x 10 ¹²
Thermal Conductivity, W/m-C (BTU-in./hr/ft²-F)	ASTM C518-98	-
Coefficient of Thermal Expansion		2.3 - 3.1 x 10 ⁻⁴ in/in/°C (1.3 - 1.7 x 10 ⁻⁴ in/in/°F)
TEMPERATURE RESISTANCE		
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)
Recommended Intermittent Use, max.		121°C (250°F)
Embrittlement	ASTM D746-98	-40°C (-40°F)
Cold Flexibility	MIL-P-12420D 1991 @ -40°C (-40°F)	Pass
FLAMMABILITY & OUTGASSING		
Flammability, mm (inches)	UL 94HBF* (File E20305) (Pass ≥)	-
	FMVSS 302 (Pass ≥)	1.1 (0.045)
	CSA Comp HBF (File 188149) (Pass ≥)	-
Fogging	SAE J-1756 3 hrs @ 100°C (212°F)	-
Outgassing, Total Mass Loss (TML) %	ASTM E595-93 24 hrs @ 125°C (257°F) @ <7 kPa (1.02 psi)	0.9
Outgassing, Collected Volatile Condensable Materials (CVCN) %		0.06
Outgassing, Water Vapor Regain (WVR) %		0.43

PROPERTY	TEST METHOD	VALUE
ENVIRONMENTAL		
Gasketing and Sealing	UL JMST2 (Consisting of UL50 & UL508) CAN/CSA-C22.2 No. 94-M91	File MH15464 -
Moisture Absorption, High Humidity Exposure, % Weight Gain, Typical	AMS 3568-95	2
Water Absorption, Immersion Testing, % Weight Gain, Typical	ASTM D570-95	5
UV Resistance	ASTM G53-96	Good
Ozone Resistance	GM 4486P-95	Pass
Corrosion Resistance	AMS 3568-91	Pass
Mildew/Bacteria Resistance	ASTM G21	Good
Staining	ASTM D925	No Stain

Notes:

‡Designed to meet UL 94 HBF based upon 2022 test criteria. As of 2023 items with nominal density $\geq 15.6\text{lb/ft}^3$ (250kg/m^3) are no longer eligible to be tested for UL 94 HBF but remain equivalent.

- "-" Represents testing not available at this time.
- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.



120 Seegers Ave, Elk Grove Village, IL 60007

Phone: 847.593.5630

srpco.com

info@srpco.com