



Product Data Sheet



PORON®
4790-92-25031-04P
Extra Soft Slow Rebound
Supported

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, kg/m ³ (lb./ft ³)	ASTM D3574-95, Test A	400 (25)
Tolerance, %		± 10
Thickness, mm (inches)		0.79 (0.031)
Tolerance, %		± 15
Standard Color (Code)		Black (04)
Compression Force Deflection, kPa (psi)	0.51 cm/min (0.2"/min) Strain Rate Force Measured @ 25% Deflection	8 - 58 (1.25 - 8.5)
Typical kPa (psi)		37 (5.3)
Compression Set, % max	ASTM D3574-95 Test D @ 23°C (73°F)	2
	ASTM D3574-95 Test D @ 70°C (158°F)	10
ELECTRICAL & THERMAL		
Dielectric Constant, K' ("DK")	ASTM D150 @ 22°C (72°F) Relative Humidity 50% for 24 hrs	1.48
Dielectric Strength, kV/m (volts/mil)	ASTM D149-97a	1969 (50)
Dissipation Factor, tan D ("DF")	ASTM D150-98	0.04
Volume Resistivity, ohm-cm (ohm-in)	ASTM D257-99	8 x 10 ¹¹ (3.2 x 10 ¹¹)
Surface Resistivity, ohm/sq.	ASTM D257-99	10 x 10 ¹¹
Coefficient of Thermal Expansion		2.3 - 3.1 x 10 ⁻⁴ in/in/°C (1.3 - 1.7 x 10 ⁻⁴ in/in/°F)
TEMPERATURE RESISTANCE		
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)
Recommended Intermittent Use, max.		121°C (250°F)
Embrittlement	ASTM D746-98	-12°C (10°F)



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2025 Rogers Corporation. All rights reserved.
 0825-PDF • Publication #17-086PC www.rogerscorp.com

PROPERTY	TEST METHOD	VALUE
OUTGASSING		
Fogging	SAE J-1756 3 hrs @ 100°C (212°F)	Pass
Outgassing, Total Mass Loss (TML) %	ASTM E595-93 24 hrs @ 125°C (257°F) @ <7 x 10 ³ kPa	1.44
Outgassing, Collected Volatile Condensable Materials (CVCN) %		0.27
Outgassing, Water Vapor Regain (WVR) %		0.44
ENVIRONMENTAL		
Moisture Absorption, High Humidity Exposure, % weight gain, typical	AMS 3568-95	2
Water Absorption, Immersion Testing, % weight gain, typical	ASTM D 570-95	14

The data mentioned above represents results of testing the PORON polyurethane foam only. PORON cellular polyurethane material is supported by being directly cast onto 0.05mm (2 mil) polyester film. By casting directly onto the film, a permanent bond is created. Please see physical property data for the film as represented by manufacturer below.

Supporting Material - Clear Polyester Film (PET)

PROPERTY	TEST METHOD	VALUE
Coefficient of Friction A/B, (Kinetic)	ASTM D1894	0.40
Density, kg/m ³ (lb/ft ³)	ASTM D1505	1395 (87.1)
Modulus, MD, kPa (psi)	ASTM D882	3.5 x 10 ⁶ (500,000)
Shrinkage, MD, % (TD)	39 min. @ 150°C (302°F)	1.2 (0.0)
Tensile Strength, MD, kPa (psi)	ASTM D882	2.1 x 10 ⁵ (30,000)
Ultimate Elongation, %	ASTM D882	150
Yield Strength (F5), kPa (psi)	ASTM D882	1.0 x 10 ⁵ (15,000)

Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.



120 Seegers Ave, Elk Grove Village, IL 60007

Phone: 847.593.5630

srpco.com

info@srpco.com