



Product Data Sheet



PORON EVExtend®
4701-43HBF

PROPERTY	TEST METHOD	VALUE	
PHYSICAL			
Description		43HBF-10	43HBF-12
Density, kg /m³ (lb. / ft³)	ASTM D 3574-95, Test A	168.2 (10.5)	192 (12)
Tolerance, %		± 10	
Thickness, mm (inches)		1.6 - 3.0 (0.063 - 0.118)	1.0 - 3.0 (0.039 - 0.118)
Tolerance, %		± 10	
Standard Color (Code)		Black (04)	
Compression Force Deflection, Range kPa (psi)	0.51 cm/min (0.2" / min). Strain Rate Force Measured @ 25% Deflection	34.5 - 69 (5 - 10)	48 - 103 (7 - 15)
Typical kPa (psi)		49 (7.1)	80 (11.6)
Compression Set, % max.	ASTM D 3574-95 Test D @ 23°C (73°F) ASTM D 3574-95 Test D @ 70°C (158°F)	--- 10	
Tensile Strength, Min. kPa, (psi)	ASTM D 3574-75 Test E	552 (80)	
Tensile Elongation, % min.	ASTM D 3574-75 Test E	80	
Tear Strength, kN/m, (pli) min.	ASTM D 264-91 Die C	1.75 (9)	
ELECTRICAL & THERMAL			
Thermal Conductivity, W/m-C (BTU-in./hr/ft²-F)	ASTM C 518-98	0.50 (0.35)	0.052 (0.36)
Dielectric Strength, volts/mil	ASTM D 150 @ 22°C (72°F) relative humidity 50% for 24 hrs	56	



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Materials for each application. The Rogers logo, PORON, PORON EVExtend, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2025 Rogers Corporation. All rights reserved. 0825- PDF Publication #17-427PC www.rogerscorp.com

PORON EVExtend 4701-43HBF, cont'd

PROPERTY	TEST METHOD	VALUE
TEMPERATURE RESISTANCE		
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)
Recommended Intermittent Use, max.		121°C (250°F)
Embrittlement	ASTM D 746-98	-20°C (-4°F)
FLAMMABILITY & OUTGASSING		
Flammability, mm (inches)	UL 94HBF (File 20305) (Pass ≥)	1.6 (0.063)
	UL 94HF1 (File 20305) (Pass≥)	1.0 (0.039)
Outgassing, Total Mass Loss (TML), %	Internal Method 24 hrs @ 125°C (257°F)	0.73
Outgassing, Water Vapor Regain (WVR), %		0.66
ENVIRONMENTAL		
Water Absorption, High Humidity Exposure, % weight gain, typical	AMS 3568	2
Water Absorption, Immersion Testing, % weight gain, typical	ASTM D 570-95	20

Product is supplied on a release PET.

Thickness availability may vary by construction type. Contact your local sales or customer service representative.

Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.
- First version TDS is based upon limited qualification data and will be updated over time as more materials are produced.



120 Seegers Ave, Elk Grove Village, IL 60007

Phone: 847.593.5630

srpco.com

info@srpco.com