



## Product Data Sheet



# PORON® OLED Back Pad 79SE4 Series

PORON® OLED 79SE4 Series materials provide protection in back pad displays and are self-adhesive.

PROPERTY	TEST METHOD	VALUE	
<b>PHYSICAL</b>		79SE4F-30	79SE4T-30
Density, kg/m <sup>3</sup> (lb./ft <sup>3</sup> )	ASTM D 3574-95, Test A	480 (30)	
Tolerance, %		± 10	
Thickness - FAL & Foam, mm (inches)	With Digital Tester (ONO SOKKI)	0.10 - 0.13 (0.004 - 0.005)	0.15 - 0.30 (0.006 - 0.012)
Tolerance, %		± 15	± 10
Standard Color (Code)		Gray (90)	
Peel Adhesion, with SUS, gf/in	ASTM D 1000 180° Peel	400 - 800	
Compression Force Deflection, typical, kPa (psi)	Modified ASTM D 3574 PTP-0033 @ 25% deflection	106.9 (15.5)	124 (18)
	Modified ASTM D 3574 PTP-0033 @ 50% deflection	572.2 (83)	441 (64)
Shelf Life, months		12 *From date of manufacture	

\* Storage in the original packaging located in a dry cool environment is recommended.

## PRODUCT STRUCTURE

### Structure:



### Description

①	PU Foam
②	Black PET
③	Adhesive
④	Release PET

### Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specific limits.



120 Seegers Ave, Elk Grove Village, IL 60007

Phone: 847.593.5630

[srpco.com](http://srpco.com)

[info@srpco.com](mailto:info@srpco.com)



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers PORON products for each application. The Rogers logo, PORON and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2025 Rogers Corporation. All rights reserved. 0825-PDF • Publication #17-417PC [www.rogerscorp.com](http://www.rogerscorp.com)