



Product Data Sheet

PORON® 4790-79TS5B-25 Series-04

Display Back Pad-Self-Adhesive

PROPERTY		TEST METHOD		TYPICAL VALUE		
FOAM	PHYSICAL			79TS5B-25006	79TS5B-25008	79TS5B-25012
	Density, kg/m ³ (lb./ft ³)	ASTM D3574-95, Test A		400 (25)		
	Tolerance, %			±10		
	Thickness, Foam & FAL, mm (inches)			0.15 (0.006)	0.20 (0.008)	0.30 (0.012)
	Tolerance, %			± 15	± 15	± 15
	Standard Color (Code)			Black (04)		
	Compression Force Deflection, kPa (psi)	0.51 cm/min (0.2"/min) Strain Rate Force measured @ 25% Deflection		10~35 (1.5~5)		
	Peel Adhesion, gf/in	ASTM D1000 82°C (180°F) Peel		≥ 200		
	Shelf Life, months	From date of manufacture		12		

PORON® Back Pad materials utilize an acrylic pressure sensitive adhesive manufactured to Rogers' specifications. This adhesive provides reliable bonding to a wide variety of substrates, exhibits high quality optical clarity, withstands a wide range of temperatures and is resistant to chemical exposure.

Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.



120 Seegers Ave, Elk Grove Village, IL 60007

Phone: 847.593.5630

srpco.com

info@srpco.com



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2025 Rogers Corporation. All rights reserved. 0725-PDF • Publication #17-379PC www.rogerscorp.com