

## SSP2551

# **Corrosion Resistant Fluorosilicone Shielding Elastomer**

#### PRODUCT DESCRIPTION

SSP2551 is a 72 durometer fuel and solvent resistant fluorosilicone that is filled with nickel plated aluminum particles. This product is supplied as fully cured, conductive sheet stock, continuous extrusion profiles, or ready-to-mold compound.

DATA	Method	Typical Values
<b>Shore A</b> (62-82 range)	ASTM D2240	69
Tensile psi (150 minimum)	ASTM D412	200 psi
Elongation % (50 min)	ASTM D412	350%
<b>Tear "B" ppi</b> (35 min)	ASTM D624	50
Specific Gravity (1.80 – 2.30)	ASTM D792	2.15
Compression Set % 70 hrs @ 100C (30 max)	ASTM D395	18
Volume Resistivity ohm / cm (0.250 max)	ASTM D991	0.03 ohm /cm
Shielding Effectiveness 20MHZ-10GHZ	MIL-DTL-83528	> 112 dB
Shielding Effectiveness 10GHZ-40GHZ	MIL-DTL-83528	> 100 dB
Color	-	Dark Gray
Thermal Stability Range	-	-60°C - 220°C
Galvanic Corrosion 168 Hour Salt Spray	ASTM B117	0.10%

## **CATALYZING**

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

### SHELF LIFE

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

### **HANDLING & SAFETY**

SDS information is available on request.

For more information visit www.sspinc.com. To order call (518) 885-8826/ or Fax (518) 885-4682.

## **Specialty Silicone Products, Inc.**

Corporate Technology Park \* 3 McCrea Hill Road \* Ballston Spa, NY 12020

Specialty Silicone Products, Inc is an ISO 9001:2008 registered company.

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.