

expansil™

Silicone Sponge Extrusions

AFS400


Silicone
Engineering Ltd

suraSil™AFS has been specially formulated to meet the Ministry of Defence AFS 1682A specification and the related MSRR 9481 Rolls Royce specification.

Commonly used as high temperature seals, profiles and joined rings, where low compression set is required in Aerospace and Defence sectors.



BENEFITS



Temperature range

-60°C to 230°C
(-76°F to 446°F)



Environmental resistance

Ozone, UV and weather resistant



Flame retardant

UL94HB
FAR 25/JAR 25



Long life service

vs
other elastomers

AVAILABILITY

Tubes, Cords, Profiles, Strips & Sections

Pressure Sensitive Adhesive (PSA)

Joined Rings & Gaskets

Standard Colours: White

ACCREDITATIONS

UL94HB

UL94 Horizontal Burn
Flammability Test
(Not Listed)

FMVSS 302

Federal Motor Vehicle
Safety Standard

FAR 25/
JAR 25

Flame Test for Aerospace
Applications

Silicone
Engineering Ltd

expansil™

Silicone Sponge Extrusions

AFS400

Silicone
Engineering Ltd

MECHANICAL PROPERTIES

Property	Units	Typical Value	Test Method
Density (*Measured on 25mm cord sample)	kg/m ³ (lb/ft ³)	400 (25)	ISO 845
Compression Force Deflection (CFD) 40%	KPa (psi)	175 (25.4)	ISO 3386 Part 1, 2
Tensile Strength	MPa (psi)	1.7 (246.6)	ISO 1798
Compression Set 25%, 72hrs @ 150°C, 48hrs recovery	%	6	ISO 1856
Compression Set (As Above) after Heat Age, 168hrs @ 150°C	%	3	ISO 1856
CFD 40%, after Heat Age for 168hrs @ 150°C	KPa (psi)	185 (26.8)	ISO 3386 Part 1, 2
Elongation	%	150	ISO 1798

CAPABILITIES

Thickness mm (inches)	Width mm (inches)	Length m (ft)
-----------------------	-------------------	---------------

GENERAL CHARACTERISTICS

Test	Typical Value	Standard
Brittle Point	-80°C (112°F)	ASTM D746
Limiting Oxygen Index	24%	BS 2782 Part 1
Thermal Conductivity	6.4x10 ⁻² W.m ⁻¹ .K ⁻¹	BS 874 Part 2
Radiation Resistance	>10 ⁵ Grays (10 ⁷ Rads) typical	

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary right are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.