

expansil™

Silicone Sponge Extrusions

FR250

Silicone
Engineering Ltd


The expansil™FR range is a flame retardant, closed cell silicone sponge, ideal for extrusions.

Formulated for use in extreme temperature applications where additional flame resistance is required.

expansil™FR range is commonly used for joined gaskets, gap fillers and flexible sealing solutions.



BENEFITS



Temperature range

-60°C to 230°C
(-76°F to 446°F)



Environmental resistance

Ozone, UV and weather resistant



Flame retardant

UL94V1
FAR 25/JAR 25



Long life service

vs
other elastomers

AVAILABILITY

Tubes, Cords, Profiles, Strips & Sections

Pressure Sensitive Adhesive (PSA)

Joined Rings & Gaskets

Standard Colours: Black, White, Grey and Natural

ACCREDITATIONS

UL94V1

UL94 V1 Flammability Test (Not Listed)

FMVSS 302

Federal Motor Vehicle Safety Standard

FAR 25
(Vertical)

Flame Test for Aerospace Applications

Silicone
Engineering Ltd

expansil™

Silicone Sponge Extrusions

FR250

Silicone
Engineering Ltd

MECHANICAL PROPERTIES

Property	Units	Typical Value	Test Method
Density (*Measured on 25mm cord sample)	kg/m ³ (lb/ft ³)	250 (15.6)	ISO 845
Hardness	Shore OO (Sh A)	48.5 (9.6)	ASTM D2240
Compression Force Deflection 40%	KPa (psi)	92 (6.4)	ISO 3386
Tensile Strength	MPa (psi)	0.53 (77)	ISO 1798
Elongation to Failure	%	108	ISO 1798
Compression Set 50%, 24hrs recovery, 22hrs @ 70°C	%	2.3	ISO 1856
Compression Set 50%, 24hrs recovery, 22hrs @ 100°C	%	5	ASTM D1056
Water Absorption	%	< 5	ASTM D1056

CAPABILITIES

Thickness mm (inches)

Width mm (inches)

Length m (ft)

GENERAL CHARACTERISTICS

Test	Typical Value	Standard
Brittle Point	-80°C (112°F)	ASTM D746
Limiting Oxygen Index	24%	BS 2782 Part 1
Thermal Conductivity	6.4x10 ⁻² W.m ⁻¹ .K ⁻¹	BS 874 Part 2
Radiation Resistance	>10 ⁵ Grays (10 ⁷ Rads) typical	

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary right are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.