

expansil™

Sponge Extrusion Flame Retardant

V-0 Medium-Firm

Silicone
Engineering Ltd


expansil™V-0 Medium-Firm is a flame retardant, closed cell silicone sponge.

Formulated for use in applications where high flame resistance and low smoke toxicity is critical such as Mass Transit, Aerospace, Automotive/EV and Electronic sectors.

expansil™V-0 is commonly used as sealing profiles.



BENEFITS



Temperature range

-60°C to 230°C
(-76°F to 446°F)



Environmental resistance

Ozone, UV and weather resistant



Flame retardant

UL94V0
(>1.5mm)



Long life service

vs
other elastomers

AVAILABILITY

Cords, Profiles, Strips & Sections
Pressure Sensitive Adhesive (PSA)
Joined Rings & Gaskets
Standard Colour: Grey

ACCREDITATIONS

UL94V0

UL94 Vertical Burn
Flammability Test

EN45545-2

European Railway
Standard for Fire Safety

NFPA 130

US Standard for Transit
and Passenger Rail
Systems

Airbus
ABD0031

Airbus Fire Test for
Aircraft Materials

Capable of meeting: ASTM D1056 2A4 and 2D4, ASTM D6576 Grades B & C (Medium-Firm)

Silicone
Engineering Ltd



Sponge Extrusion Flame Retardant

V-0 Medium-Fir



MECHANICAL PROPERTIES

Property	Units	Typical Value	Test Method
Density (*Measured on 12.7mm sheet)	kg/m ³ (lb/ft ³)	450 (28)	ISO 845 (ASTM D1056)
Compression Force Deflection 25% Strain	KPa (psi)	100 (14.5)	ASTM D1056
Compression Force Deflection 40% Strain	KPa (psi)	225 (32.6)	ISO 3386 part 1,2
Tensile Strength	MPa (psi)	675 (98)	ISO 1798 ASTM D412
Elongation to Failure	%	90	ISO 1798 ASTM D412
Compression Set 50%, 24hrs recovery, 22hrs @70°C	%	< 1	ISO 1856
Compression Set 50%, 24hrs recovery, 22hrs @100°C	%	3	ISO 1856
Thermal Conductivity	W/m.K	0.138	DIN EN993-15
Water Absorption	%	< 2	ASTM D1056

CAPABILITIES

Thickness mm (inches)

Width mm (inches)

Length m (ft)

GENERAL CHARACTERISTICS

Test	Typical Value	Standard
Brittle Point	-80°C (112°F)	ASTM D746
Limiting Oxygen Index	24%	BS 2782 Part 1
Thermal Conductivity	6.4x10 ⁻² W.m ⁻¹ .K ⁻¹	BS 874 Part 2
Radiation Resistance	>10 ⁵ Grays (10 ⁷ Rads) typical	

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary right are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.